



Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01432

T 978.391.4700  
F 978.391.4705

## 106-32

### SNAP CURE, HI-TEMP, ELECTRICALLY CONDUCTIVE ADHESIVE

**DESCRIPTION:** 106-32 is a fast curing, single component, silver filled, electrically conductive epoxy adhesive suitable for application by stamping, screen printing, dipping and syringe dispensing. This product is designed for assembling electrical and electronic components. The cure schedule allows for rapid processing and the resulting bond exhibits excellent thermal stability and adhesion at high temperatures.

#### TYPICAL CURED PROPERTIES:

|                               |              |
|-------------------------------|--------------|
| Consistency                   | Smooth Paste |
| Filler                        | Silver       |
| Percent Silver, cured         | > 81         |
| Glass Trans. Temp. (°C)       | > 200        |
| Volume Resistivity (ohm-cm)   | 0.00007      |
| Solderable                    | No           |
| Hydrolytic Stability          | Excellent    |
| Useful Temperature Range (°C) | -55 to +230  |
| Thermal Stability (°C)        | Good to 325  |
| T-Shear Strength (psi)        | 1875         |

**SUGGESTED HANDLING & CURING:** 106-32 is ready to use as supplied. Apply adhesive to surface to be bonded by hand and/or automatic method and assemble. Apply slight pressure to assure good mating of surfaces and formation of fillet. Best properties for most applications result when cured for 1 - 3 minutes at 170°C to 180°C. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 120°C to 150°C. Most popular cure is 10 minutes at 150°C. Product may be snap cured at 200°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf Life - 1 weeks at 25°C; or 2 months at 5°C; or 4 months at -10°C.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.*

REVISION DATE: 6/10/98 REVISION: A