



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

112-05

ANISOTROPIC CONDUCTIVE THERMOPLASTIC ADHESIVE

DESCRIPTION: 112-05 is screen-printable, anisotropic, conductive hot melt adhesive. This product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to flexing and creasing. The product can be rebonded many times by simply adding heat and slight pressure. Applications for 112-05 include, but are not limited to, conductive splicing of ribbon cables, PTF circuits, and electrical attachment of surface mounted devices. This product is useful in application where shorts between closely spaced contacts is a concern. 112-05 is a screen-printable version of 111-29.

TYPICAL CURED PROPERTIES:

Volume Resistivity (Ω -cm)	
(X, Y Axis)	1×10^{12}
(Z Axis)	0.0001
Consistency	Smooth paste
Crease Resistance	Excellent
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to 140
Peel Strength (lbs./inch)	9 - 11

HANDLING & CURING: 112-05 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI Thinner # 113-12. Apply thin film of adhesive to one or both surfaces to be bonded. Apply adhesive to a total dry thickness of 0.6 - 1.3 mils. Dry at room temperature for approximately 30 to 40 minutes, or 1-3 minutes at 120 $^{\circ}$ C. Place the two surfaces together and cure in a heat-sealing press for 5-7 seconds @ 175 $^{\circ}$ C using 100 - 150 psi to hold the surfaces tightly together. End user is advised to experimentally determine pressure, temperature and time best suited for individual applications. (See back of sheet for step-by-step directions.)

STORAGE: Shelf life: 2 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 9 months at -10 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.

SUGGESTED PROCEDURE FOR APPLYING 112-05

1. As with all adhesive bonds, surface preparation is a vital part of the process. Carefully clean both surfaces to be bonded with MEK if possible. If MEK is not compatible with the surfaces to be bonded, another suitable solvent may be substituted.
2. Allow cleaned surfaces to dry for approximately 2-3 minutes.
3. Apply CMI#112-05 to both surfaces to be bonded by means of a suitable technique (i.e. screen-printing, syringe dispensing, brushing, spraying, etc.). The thickness range for good bonding is typically 0.6 mils to 1.3 mils for most surfaces, but is influenced by the geometry of the surfaces. The end user is encouraged to experimentally determine the best thickness for each individual application.
4. Allow CMI#112-05 to dry at room temperature until it is tack-free to the touch. (A slightly elevated temperature may be used if needed.) The time will vary depending on the thickness, but usually is approximately 30-40 minutes. 112-05 can also be dried for 1-3 minutes at 120°C.
5. Place the two surfaces together and cure in a heat-sealing press for 5-7 seconds @ 175°C using enough pressure (100 - 150 psi) to hold the surfaces tightly together. End user is advised to experimentally determine pressure, temperature and time best suited for individual applications.
6. Allow to cool to room temperature under the same pressure.
7. Remove pressure. Part is ready for use.

REVISION DATE: 5/29/06 REVISION: C