

Creative Materials, Inc. 12 Willow Road Ayer, MA 01432 ISO 9001 CERTIFIED

T 978.391.4700 F 978.391.4705

## 114-26 A

## **ELECTRICALLY CONDUCTIVE POLYMER COATED FILM**

**DESCRIPTION**: 114-26 A is a medical grade, electrically conductive, polymer coated polyester film composition. It is typically used as a component for fabricating electrodes in medical testing applications. This product has been formulated to have improved conductivity and high electrical dissipation properties. Some added applications for 114-26 A include, but are not limited to, emi/rfi shielding, polymer thick film circuitry, membrane switches and electrical static dissipation. 114-26 A is available in rolls ranging in widths up to 20 inches and lengths up to 2000 feet.

## **PHYSICAL DATA:**

Substrate Type Polyester Film
Substrate Thickness (mils) 3.5 to 4.5
Conductive Coating CMI #113-09

Conductive Coating Type Silver/ Silver Chloride

Conductive Coating Thickness, min. (mils) 0.4-0.5 Crease Resistance Excellent Volume Resistivity, max. ( $\Omega$ -cm) 8.0 x 10<sup>-5</sup>

Sheet Resistivity, max. (0-sq) 0.1

Sheet Resistivity, max.  $(\Omega$ -sq) 0.1 Solderable No

Useful Temperature Range (°C) -55 to > 100 Ph (water extraction) 5.0 to 7.0

Adhesion (CMI TM-14) Class 3B or better

Shelf Life (as supplied) 2 years or more