



141 Middlesex Road (RT. 3A) • Tyngsboro, MA 01879 • (978) 649-4700 • FAX (978) 649-2040 • www.creativematerials.com

119-19

PAD PRINTABLE ELECTRODE INK

DESCRIPTION: 119-19 is a pad printable, electrically conductive, medical grade ink, and coating, suitable for application by pad printing, dipping and syringe dispensing. This product features excellent adhesion to Kapton, Mylar, glass and a variety of other surfaces. Unlike conventional conductive materials, this product is very resistant to flexing and creasing. Some applications for 119-19 include, but are not limited to, EMI/RFI shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches, electrical attachments for surface mounted devices, and anode coatings for tantalum capacitors as well as medical electrode applications. 119-19 is a higher viscosity version of 119-10.

TYPICAL CURED PROPERTIES:

Consistency	Smooth Paste
Filler	Silver/ Silver Chloride
Percent Filler, cured	> 75
Crease Resistance	Excellent
Volume Resistivity (Ω -cm)	0.0002
Sheet Resistivity (Ω /sq.)	0.075
Glass Transition Temperature	75°C
Hydrolytic Stability	Excellent
Useful Temperature Range (°C)	-55 to +200
Thermal Stability (°C)	Good to 325

SUGGESTED HANDLING & CURING: 119-19 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI Thinners #113-39, 114-20, or 114-28. Prior to using, be certain to resuspend filler. Best properties, for most applications, result when cured for 20 minutes at 175°C. Good properties are obtained on a variety of substrates by dry and curing at temperatures ranging from 50°C to 180°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf Life: 12 months at -10°C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 6/5/97 REVISION: A