



Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01432

T 978.391.4700  
F 978.391.4705

**119-32**

**WATERBORNE, LOW V.O.C., SPRAYABLE, CONDUCTIVE INK & COATING**

**DESCRIPTION:** 119-32 is a waterborne, low V.O.C., electrically conductive ink and coating suitable for application by spraying. This product features adhesion to Kapton, Mylar, glass, and a variety of other surfaces. Unlike conventional conductive materials, this product is very resistant to flexing and creasing. Some applications for 119-32 include, but are not limited to, medical electrodes, EMI/RFI shielding, polymer thick film circuitry, membrane switches and static elimination.

**TYPICAL CURED PROPERTIES:**

Consistency	Thin Liquid
Crease Resistance	Excellent
Volume Resistivity ( $\Omega$ -cm)	0.00015
Sheet Resistivity, max. ( $\Omega$ /sq./mil.)	0.06
Solderable	No
Hydrolytic Stability	Excellent
Useful Temperature Range ( $^{\circ}$ C)	-55 to +140
Thermal Stability ( $^{\circ}$ C)	Good to 175
Coverage (sq. ft./gal. at 1.0 mils dry)	300.79
V.O.C.'s (grams/liter)	60.8

**SUGGESTED HANDLING & CURING:** Before using mix well to re-suspend filler. Further thinning may be accomplished by adding small amounts of distilled water. Best properties are obtained on a variety of substrates by curing for 10 minutes at 125 $^{\circ}$ C. Good properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 150 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf Life: 6 months at 21 $^{\circ}$ C. DO NOT ALLOW TO FREEZE.

**SAFETY & HANDLING:** Wash with soap and water to remove from skin.