



141 Middlesex Road (RT. 3A) • Tyngsboro, MA 01879 • (978) 649-4700 • FAX (978) 649-2040 • www.creativematerials.com

## 120-14

### 7 OHM/SQ/MIL CONDUCTIVE INK

**DESCRIPTION:** 120-14 is an electrically conductive ink/coating for application by screen-printing, dipping and syringe dispensing. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion, scratching, flexing and creasing. Some applications for 120-14 include, but are not limited to, heater panels, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, and membrane switches.

#### **TYPICAL PROPERTIES:**

Viscosity (cps)	100,000- 130,000
Filler	Carbon/Silver
Crease Resistance	Excellent
Volume Resistance, max. ( $\Omega$ -cm)	0.018
Sheet Resistivity, max. ( $\Omega$ /square/mil)	7
Hydrolytic Stability	Excellent
Useful Temperature Range ( $^{\circ}$ C)	-55 to 200

**SUGGESTED HANDLING & CURING:** 120-14 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner #112-19. Prior to use, be certain to mix well to resuspend fillers. Best properties, for most applications, result when cured for 5 minutes at 120 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 175 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf life: 2 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.*

REVISION DATE: 7/22/98 REVISION: A