



Creative Materials, Inc.
141 Middlesex Road
Tyngsboro, MA 01879

T 978.649.4700
F 978.649.2040

123-23

250,000 OHM/SQUARE INK & COATING

DESCRIPTION: 123-23 is a carbon-based, electrically conductive ink, coating and adhesive suitable for application by stamping, screen printing, dipping and syringe dispensing. This product has excellent thermal stability and features excellent adhesion to Kapton®, Mylar®, glass and a variety of other surfaces. Unlike conventional conductive materials, this product is very resistant to flexing and creasing. Some applications for 123-23 include, but are not limited to, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches, electrical attachments and static elimination. 123-23 can be blended with CMI's 112-48 (20 Ω/square), 112-15 (0.010 Ω/square), or 112-47 (25,000Ω/square) in any ratio to obtain in-between electrical conductivity.

TYPICAL CURED PROPERTIES:

Consistency	Smooth Paste
Filler	Carbon
Crease Resistance	Excellent
Volume Resistivity (Ω-cm)	630
Sheet Resistivity (Ω/sq)	250,000
Solderable	No
Hydrolytic Stability	Excellent
Useful Temperature Range (°C)	-55 to +200
Thermal Stability (°C)	Good to 325

SUGGESTED HANDLING & CURING: 123-23 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI Thinner#112-19. Best properties, for most applications, result when cured for 5 minutes at 125°C. Good properties are obtained on a variety of substrates by dry and curing at temperatures ranging from 50°C to 150°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf Life: 6 months at 21°C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 11/12/09 REVISION: B