



Creative Materials, Inc.  
141 Middlesex Road  
Tyngsboro, MA 01879

T 978.649.4700  
F 978.649.2040

**123-38A/B-187**

**EXTREMELY THERMALLY CONDUCTIVE, EPOXY POTTING COMPOUND**

**DESCRIPTION:** 123-38A/B187 is a nitride filled, two component, underfill, epoxy potting and encapsulating compound. Product is designed to release entrapped air rapidly during cure, resulting in a smooth, pinhole free surface. For underfilling applications, low viscosity makes this product ideal.

	<u>Part A</u>	<u>Part B 187</u>	<u>Mixture</u>
Appearance:	Grey	Amber	Grey
Viscosity (cps):	2000	500	3100
Mix Ratio (By Weight):	100	3	----
Pot Life:	----	----	> 4 Hrs

**MIXING INSTRUCTIONS:** Premix Part A in original container prior to adding curing agent. Add Part B to Part A and mix until uniform. **NOTE:** It is not unusual for crystallization of the B-187 to occur. Warm to 40-45°C in a water bath to return the material to it's original viscosity. The crystallization of the catalyst does not affect the performance of the product in any way. To prevent re-crystallization, store the B-187 at temperatures between 35-45°C.

**CURING INSTRUCTIONS:**

Handling Properties:	30 min @ 80°C
Full Cure:	1 hr @ 80°C or 30 min @ 100°C

**TYPICAL CURED PROPERTIES:**

Hardness (Shore D)	> 85
Coef. of Therm. Exp. (in/in/°C x 10 <sup>-6</sup> )	42
Therm. Cond. (W/mK)	1.34
Cure Shrinkage (%)	0.394
Heat Distortion Temp. (°C)	115
Tensile Strength (psi)	9600
Water Absorption (%)	< 0.22
Dielectric Strength (volts/mil)	475
Volume Resistivity (Ω-cm)	1 x 10 <sup>15</sup>
Power Factor (60 HZ)	0.028
Dielectric Constant (60 HZ)	4.3

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.*

REVISION DATE: 10/9/07 REVISION: C