

Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

125-14

15,000 OHM/SQUARE INK & COATING

DESCRIPTION: 125-14 is a carbon-based, electrically conductive ink and coating suitable for application by stamping, screen printing, dipping and syringe dispensing. This product has improved thermal stability compared to 111-26 and features excellent adhesion to Kapton®, Mylar®, glass and a variety of other substrates. Unlike conventional conductive materials this product is very resistant to flexing and creasing. Some applications for 125-14 include, but are not limited to printed heaters, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches, electrical attachments and static elimination. 125-14 can be blended with CMI's 126-48 (50 Ω /square) in any ratio to obtain in-between electrical conductivity.

TYPICAL PROPERTIES:

Viscosity (cps)	30,000 – 45,000
Filler	Carbon
Crease Resistance	Excellent
Volume Resistivity (Ω -cm)	38
Sheet Resistivity (Ω /sq.)	15,000
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to +180
Thermal Stability ($^{\circ}$ C)	Good to +230

SUGGESTED HANDLING & CURING: 125-14 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner 112-19. Prior to use, be certain to mix well to re-suspend fillers. Best properties, for most applications, result when cured for 5 minutes at 125 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 175 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: up to 2 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -20 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 07/31/20 REVISION: C