

Creative Materials, Inc. 12 Willow Road Ayer, MA 01432 ISO 9001 CERTIFIED

T 978.391.4700 F 978.391.4705

125-32

SCREEN-PRINTABLE, ELECTRICALLY CONDUCTIVE INK

<u>DESCRIPTION</u>: 125-32 is a screen-printable, electrically conductive ink, coating and adhesive suitable for application by stamping, screen printing, dipping and syringe dispensing. This product features excellent adhesion to Kynar, Kapton, Mylar, glass and a variety of other surfaces. Unlike conventional conductive materials, this product is very resistant to flexing and creasing. Some applications for 125-32 include, but are not limited to, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches, electrical attachments for surface mounted devices, and anode coatings for tantalum capacitors.

TYPICAL CURED PROPERTIES:

Viscosity (cps.) 9,600
Filler Carbon
Crease Resistance Excellent

Sheet Resistivity (ohm/sq./mil)

20 min. at 175°C: <40
Solderable No
Hydrolytic Stability Excellent
Useful Temperature Range (°C) -55 to +200
Thermal Stability (°C) Good to 325

SUGGESTED HANDLING & CURING: 125-32 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of thinner #120-08. Prior to using, be certain to resuspend filler. Best properties, for most applications, result when cured for 20 minutes at 170°C to 180°C. Good properties are obtained on a variety of substrates by dry and curing at temperatures ranging from 50°C to 150°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf Life - 6 months at 25°C; or 9 months at 5°C; or 12 months at -10°C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.