



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

126-29Y

YELLOW CONDUCTIVE INK

DESCRIPTION: 126-29Y is a yellow electrically conductive ink/coating for application by screen-printing, dipping and syringe dispensing. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion, scratching, flexing and creasing. Some applications for 126-29Y include, but are not limited to, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, and membrane switches. 126-29Y is a more conductive yellow version of 112-48.

TYPICAL PROPERTIES:

Color	Yellow
Viscosity (cps)	30,000 – 35,000
Filler	Silver
Crease Resistance	Excellent
Volume Resistance, max. (Ω -cm)	0.0125
Sheet Resistivity (Ω /square/mil)	<5.0
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to 200

SUGGESTED HANDLING & CURING: 126-29Y is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner 112-19, 113-12, and/or n-Methyl Pyrrolidone. Prior to use, be certain to mix well to re-suspend fillers. **Best properties**, for most applications, result when cured for 3 to 5 minutes at 110 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 175 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 2 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.

REVISION DATE: 09/12/14 REVISION: A