



**CREATIVEMATERIALS**

Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01432

[www.creativematerials.com](http://www.creativematerials.com)

ISO 9001 CERTIFIED  
ISO 14001 CERTIFIED

T 978.391.4700  
F 978.391.4705

## 126-33

### EXTREMELY CONDUCTIVE INK

**DESCRIPTION:** 126-33 is an ink/coating with extremely high electrical conductivity for application by screen-printing, dipping and syringe dispensing. The product features excellent adhesion to Kapton, Mylar, and a variety of other substrates. **The superior conductivity of this product allows the end user to print narrower and/or longer circuit trace lines or thinner coatings without compromising overall maximum ohm values.** The proper use of this feature can result in a significant cost saving or enhanced performance. Unlike conventional conductive materials, this product is resistant to aggressive solvents such as MEK and acetone. Some applications for 126-33 include, but are not limited to, RFID antennae, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, and membrane switches.

#### TYPICAL PROPERTIES:

Viscosity (cps)	35,000
Filler	Silver
Percent Silver (cured)	> 84
Volume Resistance, max. ( $\Omega$ -cm)	0.00002
Sheet Resistivity ( $\Omega$ /square/mil)	0.008
Hydrolytic Stability	Excellent
Useful Temperature Range ( $^{\circ}$ C)	-55 to +200

**SUGGESTED HANDLING & CURING:** 126-33 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner 102-03 or Isophorone. Prior to use, be certain to mix well to re-suspend silver. **Best properties** for most applications result when cured for 3 to 5 minutes at 175 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 110 $^{\circ}$ C to 180 $^{\circ}$ C. Not recommended for applications that cannot cure above 110 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf life: 4 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.*

**REVISION DATE: 08/29/22 REVISION: C**