



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

www.creativematerials.com

ISO 9001 CERTIFIED

T 978.391.4700
F 978.391.4705

126-47 FLEXIBLE THERMALLY CONDUCTIVE ADHESIVE

DESCRIPTION: 126-47 is a screen printable flexible thermally conductive adhesive. This product features excellent adhesion to Kapton®, Mylar®, glass and a variety of other substrates. Unlike conventional materials, this product is very resistant to flexing and creasing. Product can be re-bonded many times by simply applying heat and slight pressure. Some applications for 126-47 include, but are not limited to, printed circuit board fabrication, advanced material composites, and thermal management. 126-47 is useful for applications requiring flexibility at very low temperatures. 126-47 is a thermally conductive version of 124-33.

TYPICAL CURED PROPERTIES:

Viscosity	45,000 cps
Filler	Aluminum Nitride
Crease Resistance	Excellent
Thermal Conductivity (W/m-K)	2.5
Volume Resistance (Ω -cm)	1×10^{16}
Dielectric Constant (1 KHz)	4.1
Dielectric Constant (1 MHz)	3.9
Dissipation Factor (1 KHz)	0.027
Dissipation Factor (1 MHz)	0.038
Hydrolytic Stability	Excellent
Useful Temperature Range (°C)	-55 to +120
Thermal Stability (°C)	Good to +180

SUGGESTED HANDLING & CURING: 126-47 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner 102-03 or 113-12. Prior to using, be certain to re-suspend filler. Best properties, for most applications, result when dried several minutes at 100°C followed by curing for 5-10 minutes at 175°C. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 50°C to 175°C. When used as a sealant, apply adhesive to surfaces to be bonded and dry for several minutes at 150°C, then place substrates together while heating and applying slight pressure. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 6 months at 25°C; or 9 months at 5°C; or 12 months at -10°C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.

REVISION DATE: 03/16/17 REVISION: B