



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.2040

128-25A/B

SOLVENT-RESISTANT DIELECTRIC INK

DESCRIPTION: 128-25 is an opaque blue, two component, solvent-resistant, electrically insulating ink, coating and adhesive suitable for screen printing. This product features excellent adhesion to Kapton, Mylar, glass, polycarbonate and a variety of other substrates. Unlike conventional dielectric materials, this product is very resistant to methyl ethyl ketone or acetone. It is also very resistant to scratching and creasing. Some applications for 128-25 include, but are not limited to, dielectric insulation of thick film circuitry, imparting moisture resistance, arc track resistance, and weathering resistance of electrical/electronic devices.

TYPICAL CURED PROPERTIES:

Viscosity (cps)	10,000 – 15,000
Volume Resistivity (ohm-cm)	1x10 ¹⁶
Dielectric Constant (50 Hz)	4.0
Hydrolytic Stability	Excellent
Useful Temperature Range (°C)	-55 to +200
Thermal Stability (°C)	Good to +280

MIXING INSTRUCTIONS: Premix 128-25 Part A, in original container prior to adding curing agent. Add Part B119-44 and mix until uniform. At this point the material may be thinned by adding small amounts of CMI 113-12 thinner.

CURING INSTRUCTIONS:

	<u>Part A</u>	<u>Part B119-44</u>
Mix ratio by weight	100	2.0
Cure schedule	80°C	4 Hours
	90°C	2 hours
	100°C	1 hour
Pot-Life at	25°C	>72 hours

STORAGE: Shelf life: 12 months at 25°C, in unopened, unmixed containers

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in particular application or possible infringements on patents.

REVISION DATE: 10/25/19 REVISION: A