



Creative Materials, Inc.
141 Middlesex Road
Tyngsboro, MA 01879

T 978.649.4700
F 978.649.2040

F-947

BLACK, FLAME-OUT, EPOXY POTTING COMPOUND

DESCRIPTION: F-947 is a black, flame-out, two component, epoxy potting and encapsulating compound. Product cures at room temperature and is designed to release entrapped air rapidly during cure, resulting in a smooth, pinhole free surface.

	<u>Part A</u>	<u>Part B</u>	<u>Mixture</u>
Appearance:	Black	Amber	Black
Viscosity (cps):	55,000	300	5,000
Mix Ratio (By Weight):	100	12	----
Pot Life:	---	---	1/2 Hr

MIXING INSTRUCTIONS: Premix Part A in original container prior to adding curing agent. Add Part B to Part A and mix until uniform.

CURING INSTRUCTIONS:

Handling Properties:	2-4 hrs @ 25°C
Full Cure:	24 hrs @ 25°C or 5-15 mins @ 100°C

TYPICAL CURED PROPERTIES:

Specific Gravity	1.59
Hardness (Shore D)	> 85
Coef. of Therm. Exp. (in/in/°C x 10 ⁻⁶)	22
Therm. Cond. (W/mK)	1.28
Cure Shrinkage (%)	0.189
Heat DistortionTemp. (°C)	105
Tensile Strength (psi)	9600
Water Absorption (%)	< 0.22
Dielectric Strength (volts/mil)	475
Volume Resistivity (Ω-cm)	1 x 10 ¹⁵
Power Factor (60 HZ)	0.028
Dielectric Constant	4.3 @ 60 HZ
Useful Temperature Range (°C)	-55 to +200

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 6/17/08 REVISION: D