



Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01432

T 978.391.4700  
F 978.391.4705

## 107-07

### ELECTRICALLY CONDUCTIVE SPRAY CONCENTRATE

**DESCRIPTION:** 107-07 is an electrically conductive spray concentrate suitable for coating electronic enclosures. This product features excellent adhesion to Kapton®, Mylar®, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion and scratching. 107-07 is one of a complete series of conductive coatings designed to bleed off electrostatic discharge while maintaining good attenuation characteristics. Some applications for 107-07 include, but are not limited to, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches, electrical attachments for surface mounted devices, and anode coatings for tantalum capacitors. 107-07 can be further cross-linked with B-187 curing agent for applications requiring resistance to solvents and high humidity. Refer to handling instructions for additional information.

#### **TYPICAL CURED PROPERTIES:**

Consistency	Smooth Paste
Filler	Nickel
Crease Resistance	Excellent
Volume Resistance ( $\Omega$ -cm)	18.9
Sheet Resistivity ( $\Omega$ /sq./mil)	7500
Solvent Resistance	Excellent
Hydrolytic Stability	Excellent
Useful Temperature Range ( $^{\circ}$ C)	-55 to 200
Thermal Stability ( $^{\circ}$ C)	Up to 325

**SUGGESTED HANDLING & CURING:** 107-07 is supplied in concentrate form. Further thinning may be accomplished by adding small amounts of MEK, CMI Thinner #203, and/or butyl cellosolve acetate. Prior to using, be sure to resuspend nickel. Best properties, for most applications, result when cured for 5-10 minutes at 175 $^{\circ}$ C. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 150 $^{\circ}$ C. NOTE: Add 1phr B-187 catalyst when using low temperature cures. The use of B187 is suggested to impart a high degree of chemical resistance to the conductive lines. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf life: 4 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.*

REVISION DATE: 6/10/98 REVISION: A