



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

115-29

ANISOTROPIC CONDUCTIVE EPOXY ADHESIVE

DESCRIPTION: 115-29 is a screen-printable, anisotropically conductive, epoxy adhesive. This product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to heat, and thermocycling. Applications for 115-29 include, but are not limited to, conductive splicing of ribbon cables, PTF circuits, and electrical attachment of surface mounted devices. This product is useful in application where shorts between closely spaced contacts is a concern.

TYPICAL CURED PROPERTIES:

Volume Resistivity (Ω -cm) (X, Y Axis)	1×10^{12}
(Z Axis)	0.0001
Consistency	Smooth paste
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to +200
Thermal Stability ($^{\circ}$ C)	Good to 325
T-Shear Strength (psi)	1000

HANDLING & CURING: 115-29 is ready to use as supplied. Apply thin film of adhesive (0.6-1.3 mils) to one of the surfaces to be bonded. At this point, the surfaces should be pressed firmly together. Best properties, for most applications, result when cured for 30-40 minutes at 155 $^{\circ}$ C while maintaining pressure to insure proper mating. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 130 $^{\circ}$ C to 200 $^{\circ}$ C. End user is advised to experimentally determine temperature, pressure and time best suited for individual applications.

Note: It is not unusual for crystallization of the 115-29 to occur. Warm to 40-45 $^{\circ}$ C in a water bath to return the material to its original viscosity. The crystallization does not affect the performance of the product in any way.

STORAGE: Shelf life: 3 weeks at 25 $^{\circ}$ C; or 3 months at 5 $^{\circ}$ C; or 6 months at -10 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.

REVISION DATE: 3/17/94 REVISION: A