



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

119-07

PAD-PRINTABLE, HIGH DIELECTRIC STRENGTH, INK / COATING

DESCRIPTION: 119-07 is a black, pad-printable, one component, high dielectric strength, epoxy ink and coating. This product features excellent adhesion to Kapton, Mylar, aluminum, FR-4 boards, glass and a variety of other substrates. Unlike conventional dielectric materials, this product is very resistant to abrasion, scratching, and thermal aging. Applications for 119-07 include, but are not limited to, high dielectric strength coatings for electrical and electronic devices. 119-07 is designed for pad printing onto contoured surfaces.

TYPICAL PROPERTIES:

Viscosity (cps)	10,000-12,000
Dielectric Strength (Volts/0.001")	2500
Dielectric Constant (100Hz)	4.0
Volume Resistivity (ohm-cm)	1×10^{16}
Pencil Hardness	6H (min.)
Glass Transition Temperature (°C)	160
Hydrolytic Stability	Excellent

SUGGESTED HANDLING AND CURING: 119-07 is ready to use as supplied. Prior to using, be certain to re-suspend filler. Further thinning may be accomplished by adding small amounts of CMI Thinner # 113-39. Best properties, for most applications, result when cured for 1 hour at 125°C, or 30 minutes at 150°C. Good properties are obtained on a variety of substrates by curing at temperatures ranging from 125°C to 185°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 2 months at 25°C; or 6 months at -10°C.

SAFETY AND HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.