



Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01432

T 978.391.4700  
F 978.391.4705

## 119-48

### FLEXIBLE UV COATING

**DISCRIPTION:** 119-48 is a thixotropic, screen-printable, flexible, ultraviolet-cured dielectric coating. This material can be used as an electrically insulating standoff on Indium Tin Oxide, sputtered glass and polyester in Touch Screen applications. This coating can be used on a variety of substrates such as polycarbonate, treated and untreated polyesters, Kapton, epoxy/glass PC boards and glass.

#### PROPERTIES:

Color	Clear
Viscosity	100,000 to 200,000 cps
Dielectric Strength (volts/mil)	365
Volume Resistivity ( $\Omega$ -cm)	$7.1 \times 10^{15}$
Dielectric Constant (1 kHz)	4.3
Dielectric Factor (60 Hz)	0.018
Solids Content (%)	100
Specific Gravity (g/cc)	1.2
Coverage @ 1 mil. (ft <sup>2</sup> /gal.)	1600

**SUGGESTED HANDLING & CURING:** Material is ready to use as received. Store at low temperature to maintain consistent flow properties. Allow material to warm up to room temperature before opening container. Cure using a 200-300 watt/inch mercury vapor lamp. Speed of cure will vary depending upon available energy. Typical cure time ranges from a few seconds to 1 minute when work is positioned 6-10 inches from lamp. Faster curing can be accomplished by moving lamp closer to work. When applying two layers, it is sometimes desirable to under cure the first layer so as to improve interlayer adhesion.

**STORAGE:** Shelf Life: 6 months at 25°C.

**SAFETY AND HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 12/11/08 REVISION: B