

www.creativematerials.com

**ISO 9001 CERTIFIED** 

Creative Materials, Inc. 12 Willow Road Ayer, MA 01432

т 978.391.4700 **F** 978.391.4705

## 120-37A/B

## LOW DENSITY, HIGH TEMPERATURE RESISTANT, LOW SHRINKAGE, ROOM TEMPERATURE CURING, EPOXY POTTING COMPOUND

**DESCRIPTION:** 120-37A/B, is a two component, room temperature curing, low density, high temperature resistant, low shrink, syntactic foam, epoxy potting and encapsulating compound. The product is designed to release entrapped air rapidly during cure, resulting in a smooth, pinhole free surface. 120-37A/B is a room temperature curing version of 120-37A/B-187.

Part A	Part B	Mixture	
Appearance:	Black	Amber	Black
Mix Ratio (By Weight):	100	20	
Pot Life 100 gram mass:			30 minutes

**<u>MIXING</u> INSTRUCTIONS:** Premix Part A in original container prior to adding curing agent. Add Part B to Part A and mix until uniform. **NOTE:** Due to the purity of the materials it is not unusual for crystallization of the Part A to occur. Warm to 40-45°C in a water bath to return the material to it's original viscosity. The crystallization of the resin and or catalyst does not affect the performance of the product in any way.

## CURING INSTRUCTIONS:

Handling Properties:	12 hour @ 25°C
Full Cure:	24 hours @ 25°C

## TYPICAL CURED PROPERTIES:

Specific Gravity (gr./cc.)	0.96
Hardness, min. (Shore D)	80
Coef. of Therm. Exp. (in/in/°C x 10 <sup>-8</sup> )	62
Cure Shrinkage (%)	<0.22
Heat Distortion Temp. (°C)	115
Tensile Strength (psi)	6,250
Water Absorption (%)	< 0.20
Dielectric Strength (volts/mil)	475
Volume Resistivity (Ω-cm)	1 x 10 <sup>15</sup>
Power Factor (@ 60 HZ)	0.028
Dielectric Constant (@ 1 MHz)	3.0

**STORAGE:** Shelf life: 12 months at 25°C, in unopened, unmixed containers.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.