



Creative Materials, Inc.
12 Willow Road
Ayer, MA 01432

T 978.391.4700
F 978.391.4705

123-26

PRESSURE VARIABLE RESISTOR INK FOR STENCIL APPLICATION

DESCRIPTION: 123-26 is electrically conductive ink and coating that decreases in resistance as pressure is increased. This material is suitable for application by stenciling, dipping and syringe dispensing. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion, scratching, flexing and creasing. Some applications for 123-26 include, but are not limited to, pressure transducers and pressure sensitive membrane switches. 123-26 can be blended with CMI# 112-48 to alter the initial and final resistance (under pressure) of the material. 123-26 is a higher viscosity version of 118-44.

TYPICAL PROPERTIES:

Viscosity (cps)	200,000-220,000
Crease Resistance	Excellent
Sheet Resistivity without pressure (Ω /sq/mil)	10 Meg
Sheet Resistivity with pressure, as low as (Ω /sq/mil)	300K
Hydrolytic Stability	Excellent
Useful Temperature Range ($^{\circ}$ C)	-55 to 200

SUGGESTED HANDLING & CURING: 123-26 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner #112-19. Prior to use, be certain to mix well to resuspend fillers. Best properties, for most applications, result when cured for 3 to 5 minutes at 110 $^{\circ}$ C – 125 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 175 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 2 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

SAFETY & HANDLING: Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to results or possible infringements on patents.

REVISION DATE: 9/2/03 REVISION: A