



124-25

SYRINGE DISPENSE RADIO OPAQUE INK

DESCRIPTION: 124-25 is a flexible, radio opaque ink/coating for application syringe dispensing. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. Unlike conventional conductive materials, this product is very resistant to abrasion, scratching, and thermal aging. Some applications for 124-25 include, but are not limited to, manufacturing of medical devices and instruments.

PROPERTIES:

Viscosity (cps)	approx. 125,000
Percent Filler (cured)	> 80
Abrasion Resistance	Excellent
Hydrolytic Stability	Excellent
Useful Temperature Range (°C)	-55 to 200
Thermal Stability (°C)	Good to 325

SUGGESTED HANDLING & CURING: 124-25 is ready to use as supplied. **Best properties**, for most applications, result when cured for 30 minutes at 175°C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50°C to 175°C. End user is advised to experimentally determine temperature and time best suited for individual applications.

STORAGE: Shelf life: 3 months @ 25°C, or 6 months @ 5°C, or 12 months at -10°C.