



Creative Materials, Inc.  
12 Willow Road  
Ayer, MA 01879

T 978.391.4700  
F 978.391.4705

## 126-09

### ELECTRICALLY CONDUCTIVE INK/COATING

**DESCRIPTION:** 126-09 is an electrically conductive ink/coating for application by screen-printing, dipping and syringe dispensing. The product features excellent adhesion to Kapton, Mylar, glass and a variety of other substrates. This product is very resistant to abrasion, scratching, flexing and creasing and is suitable for applications requiring significant flexing cycles with minimal effect on electrical performance. Some applications for 126-09 include, but are not limited to, RFID antennae, emi/rfi shielding of polyimide flexible circuits, polymer thick film circuitry, membrane switches and coatings for tantalum capacitors.

#### TYPICAL PROPERTIES:

Viscosity (cps)	15,000-25,000
Crease Resistance	Excellent
Humidity Resistance	Excellent
Volume Resistance, max. ( $\Omega$ -cm)	<0.00013
Sheet Resistivity ( $\Omega$ /square/mil)	< 0.05
Useful Temperature Range ( $^{\circ}$ C)	-55 to 200

**SUGGESTED HANDLING & CURING:** 126-09 is ready to use as supplied. Further thinning may be accomplished by adding small amounts of CMI thinner #112-19, NMP, or EB Acetate. Prior to use, be certain to mix well to re-suspend silver. **Best properties** for most applications result when cured for 5 minutes at 120 $^{\circ}$ C. Excellent properties are also obtained on a variety of substrates by curing at temperatures ranging from 50 $^{\circ}$ C to 175 $^{\circ}$ C. End user is advised to experimentally determine temperature and time best suited for individual applications.

**STORAGE:** Shelf life: 3 months at 25 $^{\circ}$ C; or 6 months at 5 $^{\circ}$ C; or 12 months at -10 $^{\circ}$ C.

**SAFETY & HANDLING:** Use with adequate ventilation. Keep away from sparks and open flames. Avoid prolonged contact with skin and breathing of vapors. Wash with soap and water to remove from skin.

*All technical information is based on data obtained by CMI personnel and is believed to be reliable. No warranty is either expressed or implied with respect to suitability in a particular application or possible infringements on patents.*

**REVISION DATE: 06/10/13 REVISION: A**